

Products chemical resistance

Technical bulletin 2

Azo-Grout™



Azo-Grout™ products chemical resistance chart

Excellent resistance	Good resistance	Poor resistance
Ammonium Hydroxide - 10% solution	Acetic Acid - 20% solution	Calcium Hypochlorite - 5%
Barium Hydroxide	Ammonium Hydroxide	Chromic Acid
Borax Solutions	Anylacetate	Ethyl Acetate
Boric Acid Solutions	Butylacetate	Formaldehyde - 37%
Brine Solution	Chlorobenzene	Formic Acid
Calcium Bisulfite Solutions	Diesel Fuel	Hydrochloric Acid 37%
Calcium Chloride	Diethylene Glycol	Methyl Chloride
Calcium Hydroxide	Ethylene Glycol - 100%	Methyl Ethyl Keytone
Mineral Oil	Fuel Oil	Methyl Pyrrolidone
Motor Oil	Gasoline	Nitric Acid - 10%
Phosphoric Acid < 75%	Hydraulic Oils	Sodium Hydroxide - 47%
Sea Water	Linseed Oil	Sodium Hypochlorite - 5%
Soap	Lubricating Oils	Sulfuric Acid
Water	Naptha	Toluene
	Ozone	Trichlorethylene
	Potassium Hydroxide	Xylene
	Sodium Hydroxide - 20%	
	Soybean Oil	
	Tung Oil	

Note: The list presents the general effect of exposure to various chemicals at room temperature. Exposure at elevated temperature may provide different results and should be tested. The chart is to be used as a general guide. Other considerations such as application technique and general conditions may affect chemical resistance.

WARRANTY The information contained in this document is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. The customer must inspect and test our products before use, and satisfy themselves as to the contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials, and in no event shall we be liable for special, incidental or consequential damages.

©Azon 2010 TECHAG2 Page 1 of 1